

TECHNICAL DATA SHEET

info@deffner-johann.de | +49 (0)9723 9350-0

Die in diesem Produktdatenblatt genannten Spezifikationen dienen nur zur Produktbeschreibung und beziehen sich auf den Zeitpunkt unmittelbar nach der Produktion bzw. Import des Produktes. Sie entsprechen den Angaben des Herstellers. Eine rechtsverbindliche Zusicherung bestimmter Eigenschaften oder der Eignung für einen bestimmten Einsatzzweck kann hieraus nicht abgeleitet werden. Durch unsachgemäßen Transport und / oder unsachgemäße Lagerung können sich Änderungen ergeben. Die Angaben in diesem Produktdatenblatt entbinden den Verarbeiter nicht von eigener Prüfung der Eigenschaften des Produktes und dessen Eignung für die vorgesehene Verwendung.

Soft Blasting Media MK 100

Natural vegetable granules

Basic raw material

Natural annual plants

Chemical and physical properties

Colour		light brown
Structure		granules
Average particle size / particle range		100 µm - 250 µm
Oxide ash (850 °C, 4 h)	~	1 %
pH-value (10 % suspension)		4.5 - 6.5
Bulk density (in accordance with DIN EN ISO 60)		320 g/l - 420 g/l

Screen analysis (in accordance with DIN EN ISO 4610/air jet sieve) with an interior mesh aperture of:

<u>> 300 µm</u>	<u>> 50 µm</u>	<u>> 32 µm</u>
max. 1 %	92 % - 100 %	94 % - 100 %

General remarks

Soft Blasting Media MK 100 vegetable granules is an environment friendly product gained from replenishable raw materials.

As with all natural products slight differences to the above given values may arise.

Release date: 2020-11 / 1 page